

# DINITROL 6080

Fiberplast – Glass-fibre reinforced putty

Body Repair

Body Repair

## Characteristics:

DINITROL 6080 Fiberplast is a glass-fibre reinforced 2-component polyester putty.

## Application:

Rusted areas on vehicle bodywork can be bridged without glass fibre mats.  
After complete hardening, Fiberplast can be filed or finished with putty  
(i.e. DINITROL 6050 Polyplast).

## Method of Use:

The substrate must be filed and free from grease and rust. Rusted edges must be removed.  
Thoroughly mix the required amount of putty with 2 – 3% hardening paste.  
Depending on temperature and amount of hardener, the working time is approx. 5 minutes.  
Tools must be cleaned immediately after use with nitro thinner or paint thinner, given that  
once hardened, the material can no longer be removed.

## Technical data:

Raw material base:	unsaturated polyester resin
Hardening system:	Dibenzoyl peroxide paste 50%
Flash point:	> 21°C
Spec. weight:	1.24 g/ml
Working time 2% hardener:	approx. 5 mins
Complete hardening/filing	approx. 30 minutes, depending on temperature and coat thickness
Storage time:	12 months (between 15°C and 25°C)
Package size:	0.750 kg 1.5 kg

Note: Seal opened packages tightly after use.

Please refer to the safety data sheet or packaging label for safety instructions.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH  
Pyrmonter Str. 76  
D-32676 Lügde  
Telephone:  
+49 (0) 52 81 / 9 82 98-0  
Fax:  
+49 (0) 52 81 / 9 82 98-60  
Email:  
service@dinol.com