

## **GMH BLACK**

#### Description

- Nitrocellulose based industrial lacquer •
- Can be used as a guide coat •

### **Technical Summary**

- Quick drying •
- Low gloss
- Good coverage
- Easy to apply
- Ready for use •

	Working process	Nitrocellulose lacquer and as a guide coat
	Substrates:	Subframes, beneath mudguards etc.
T	Pretreatment / Cleaning:	Clean with Duxone <sup>®</sup> Wax and Grease Remover
	Application:	Use recommended respirators. Refer to relevant Material Safety Data Sheet (MSDS)
<b>∏</b> s		Ready for use, shake well before use
		1.6 – 1.8 mm 300 – 400 kPa 3 coats = approx. 10 microns
		1.8 - 2.0  mm 300 - 400  kPa 2 - 3  coats = approx. 10 microns
$\frac{1}{2}$		5 minutes / 20°C between coats
		10 minutes / 20°C







# **GMH BLACK**

### **TECHNICAL DATA**

	Flashpoint:	Approx5 °C		
	<b>Raw Material:</b>	Nitrocellulose based resins		
	Specific Gravity:	0.8 g/L		
	Approx.	$6.5 \text{ m}^2/\text{L}$ at 10 microns DFT		
	Coverage:			
	Cleaning of	Clean after use with Duxone <sup>®</sup> Acrylic Thinners		
	Equipment:			
	Important	For professional use only		
	<b>Remarks:</b>	<b>Notes:</b> 1. As Duxone <sup>®</sup> GMH Black is a fast drying		
		Nitrocellulose based lacquer, there may be a tendency		
		for this product to bloom or blush in cold weather		
		2. Not for exterior exposure		
This da	This data relates only to the material designated herein and does not apply to use in			
combina	combination with any other material or any process. The data is not to be considered as a			

warranty or quality specification and we assume no liability in connection with its use.

