DX46

2K HS STANDARD CLEAR





DESCRIPTION

DX46 2K HS Standard Clear is part of the Duxone repair system and is suitable for use in a clear-over-base system. This high solids universal clear has very good flow in application and delivers a good, long-lasting high-gloss finish. It can be air dried, dried on low bake or using IR, which can help improve a bodyshop's efficiency.

FEATURES

2:1 - no reducer
Very good flow
Fast through drying
Superb polishability
Excellent mar, chemical and weather resistance
Suitable for spot, panel and overall repairs

PRODUCT LIST

DX46 2K HS Standard Clear

DX18 Activator Slow

DX20 Activator Standard

DX24 Activator Extra Fast



DX46 2K HS STANDARD CLEAR



Product preparation - application STANDARD



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.





Duxone Basecoat: Surfaces must be dried / flashed-off in accordance with TDS before application Existing finishes: Surfaces must be sanded and degreased before application



	Spot & panel repair		Standard		Large surface	
	Volume	Weight	Volume	Weight	Volume	Weight
DX46	2	100	2	100	2	100
DX18	-	-	-	-	1	50
DX20	-	-	1	49	-	-
DX24	1	49	-	-	-	-



Pot life at 20°C: 3 hr 30 min



	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4 mm	1.8 - 2.2 bar	inlet pressure
HVLP	1.3 - 1.4 mm	0.7 bar	atomisation pressure

see manufacturer's instructions





2 coats

intermediate and final flash-off: 5 min - 10 min



	DX24	DX20	DX18
20 °C	4 hr	5 hr	6 hr
60 - 65 °C	20 min	30 min	40 min



Guideline for short wave IR equipment

Half power: 5 min Full power: 8 - 12 min

VOC compliant

This product mix is not VOC compliant.

DX46 2K HS STANDARD CLEAR



Products

DX46 2K HS Standard Clear

DX18 Activator Slow
DX20 Activator Standard
DX24 Activator Extra Fast

Product mix





Mixing ratios with special agents are available in the productmix table on Colour Room and in the specific TDS.



ISO 4: 28 - 37 s at 20°C DIN 4: 14 - 16 s at 20°C



50 - 60 μm



DX46 2K HS Standard Clear can be recoated within 24 hours, without intermediate sanding



Clean after use with a suitable solventbased guncleaner.

Remarks

- Material has to be at room temperature (18-25°C) before use.
- Allow additional time for preheating up to panel temperature.
- Surplus ready for use material should not be returned to original can.
- Close can of Activator tightly immediately after use, as this product will react with humid air and water and lose its hardening effect.
- If necessary for minor viscosity adjustments, use Duxone basecoat Thinner (maximum 5%).

DX46 2K HS STANDARD CLEAR



Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Duxone product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Duxone product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.