679S ULTRA PRODUCTIVE CLEAR





PRODUCT DESCRIPTION

Ultra Productive Clear 679S is a 2K clearcoat based on the patented Hyper Cure™ technology for spot, panel and medium-sized clear-over-base applications. It allows for very short drying times to help significantly boost productivity while delivering an excellent appearance.

Most productive non-voc clear with excellent appearance

FEATURES

- Easy to apply with excellent and smooth appearance.
- Offers excellent polishing qualities.
- Offers very fast air drying and short flash times between coats and bake cycles.
- Highly productive clear excellent balance between physical drying and cross-linking.
- Combines best of fast-dry and traditional clears.
- Fast dust-free times help prevent surface defects by air contamination.
- Helps to increase productivity whether air drying, baking at low temperatures or IR drying.





ULTRA PRODUCTIVE CLEAR

Product preparation - application STANDARD - LS



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.





Centari Basecoats: Surfaces must be dried / flashed-off in accordance with TDS before application Existing finishes: Surfaces must be sanded and degreased before application





M-6152

	Spot & panel repair		Standard		Large surface	
	Volume	Weight	Volume	Weight	Volume	Weight
679S	2	100	2	100	2	100
123S	1	51	-	-	-	-
125S	-	-	1	51	-	-
126S	-	-	-	-	1	51



Pot life at 20°C: 3 hr 30 min



	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4	1.8 - 2.2 bar	inlet pressure
HVLP	1.3 - 1.4	0.7 bar	atomisation pressure







2 coats

intermediate and final flash-off: 5 min - 10 min



	123S	125S	126S
20 °C	4 hr	5 hr	6 hr
60 - 65 °C	20 min	30 min	40 min



Guideline for short wave IR equipment

Half power: 5 min Full power: 8 - 12 min

VOC compliant

This product mix is not VOC compliant.





ULTRA PRODUCTIVE CLEAR

Product preparation - application STANDARD - MS



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.





Centari Basecoats: Surfaces must be dried / flashed-off in accordance with TDS before application Existing finishes: Surfaces must be sanded and degreased before application





	Spot & panel repair		Standard		Large surface	
	Volume	Weight	Volume	Weight	Volume	Weight
679S	3	100	3	100	3	100
256S	1	35	-	-	-	-
AK260	-	-	1	36	1	36
421R */ AB380 / XB383	0.6	19	-	-	-	-
AB380 / XB383	-	-	0.6	18	-	-
AB385 / XB387 / XB390	-	-	-	-	0.6	19

^{* 421}R is recommended for interiors and spot repair only.



Pot life at 20°C: 4 hr



	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4	1.8 - 2.2 bar	inlet pressure
HVLP	1.3 - 1.4	0.7 bar	atomisation pressure

see manufacturer's instructions





2 coats

intermediate and final flash-off: 5 min - 10 min



	256S // 421R	256S // AB380 / XB383	AK260 // AB380 / XB383	AK260 // AB385 / XB387 / XB390
20 °C	3 hr 30 min	4 hr	6 hr 30 min	7 hr 30 min
60 - 65 °C	15 min	15 min	20 min	25 min



Guideline for short wave IR equipment

Half power: 5 min Full power: 8 - 12 min

VOC compliant

This product mix is not VOC compliant.

679S



ULTRA PRODUCTIVE CLEAR

Products

679S Ultra Productive Clear

123S Fast Activator 125S Standard Activator 126S Slow Activator 256S Activator Fast AK260 High Solids Activator

421R Varispeed
AB380 MS Standard Thinner
AB385 MS HI-Temp Thinner
XB383 Standard Thinner
XB387 HI-Temp Thinner
XB390 Centari® 6000 Very Slow Thinner

Product mix





Mixing ratios with special agents are available in the productmix table on ChromaWeb and in the specific TDS.



ISO 4: 28 - 37 s at 20°C DIN 4: 14 - 16 s at 20°C



50 - 60 µm

Theoretical coverage

360 - 370 m²/l at 1 micron dry film thickness

Due to different activator characteristics and different mixing ratios of the ready-to-use mixture in some TDS versions, the theoretical coverage calculation may vary.

Note: The practical material consumption depends on several factors, e.g. geometry of the object, surface formation, application method, spray gun setting, inlet pressure, etc.



679S Ultra Productive Clear can be overcoated with itself within 24 hours, without intermediate sanding



Clean after use with a suitable solventbased guncleaner.

679S



ULTRA PRODUCTIVE CLEAR

Remarks

- · Material has to be at room temperature (18-25°C) before use.
- · Allow additional time for preheating up to panel temperature.
- Surplus ready for use material should not be returned to original can.
- Close can of Activator tightly immediately after use, as this product will react with humid air and water and lose its hardening effect.
- For Semi-Flexible systems 10% 805R Flexible Additive can be added to the base material. Activator and Thinner ratios remain equal.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Cromax product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Cromax product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.